

CLIENT: KEBONY
Hoffsveien 48
Oslo, Norway N-0377

Test Report No: RJ3936-2

Date: December 3, 2015

SAMPLE ID: The Client submitted and identified the following test material as: Kebony Radiata Pine.

SAMPLING DETAIL: Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.

DATE OF RECEIPT: Samples were received on November 30, 2015.

TESTING PERIOD: December 3, 2015.

AUTHORIZATION: Testing authorized Stig Lande.

TEST REQUESTED: Perform standard flame spread and smoke density developed classification tests on the sample supplied by the Client in accordance with ASTM Designation E84-15a, "Standard Method of Test for Surface Burning Characteristics of Building Materials". The foregoing test procedure is comparable to UL 723, ANSI/NFPA No. 255, and UBC No. 8-1.

TEST RESULTS:	<u>Flame Spread</u>	<u>Smoke Developed</u>
	45	250

For detailed results see page 2.


CONCLUSION: The submitted material meets the requirements for a "Class B" Flame Spread. See classification requirements on page 2.

Prepared By



Brian Ortega
Test Technician

**Signed for and on behalf of
QAI Laboratories, Inc.**



Greg Banasky
Senior Technician

PREPARATION: The sample material was submitted in sufficient quantity to form a specimen, 24 inches wide by 24 feet long.

CONDITIONING: The test specimen was conditioned to a constant weight at a temperature of $73.4 \pm 5^\circ \text{F}$ ($23 \pm 2.8^\circ \text{C}$) and a relative humidity of $50 \pm 5\%$.

CEMENT BOARD PLACEMENT: The 1/4" cement boards were placed between the test specimen and the chamber lid

E 84 TEST DATA SHEET:

CLIENT: KEBONY **DATE:** 12/03/15

SAMPLE: Kebony Radiata Pine.

FLAME SPREAD:

IGNITION: 48 seconds

FLAME FRONT: 11 feet maximum.

TIME TO MAXIMUM SPREAD: 5 minutes, 24 seconds.

TEST DURATION: 10 minutes

CALCULATION: $84.57 \times .515 = 43.55$

SUMMARY: FLAME SPREAD: 45 **SMOKE DEVELOPED:** 250 (235.89)



SUMMARY OF ASTM E84 RESULTS: Because of the possible variations in reproducibility, the results are adjusted to the nearest figure divisible by 5. Smoke Density values over 200 are rounded to the nearest figure divisible by 50.

In order to obtain the Flame Spread Classification, the above results should be compared to the following table:

<u>NFPA CLASS</u>	<u>IBC CLASS</u>	<u>FLAME SPREAD</u>	<u>SMOKE DEVELOPED</u>
A	A	0 through 25	Less than or equal to 450
B	B	26 through 75	Less than or equal to 450
C	C	76 through 200	Less than or equal to 450

BUILDING CODES CITED:

1. National Fire Protection Association, ANSI/NFPA No. 101, "Life Safety Code".
2. International Building Code, Chapter 8, Interior Finishes, Section 803.



End of Report

THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.