

www.kebony.us | 833.795.8660 | info@kebony.us

1x8 Clear Rough Sawn / #1931



Actual Dimensions: 1" x 8" * Lengths: Up to 16' **

- * Width and thickness are nominal measures Actual dimension can be slightly larger
- ** Lengths vary based on availability

Quality & Appearance Upon Delivery

Knots/Pitch Pockets	May be visible and are a natural occurrence in wood
Cracks	Surface cracks and checks may be visible
Wane	May be visible on rough sawn products
Moisture Content	4-8%
Cupping	Max. 2% of width
Density	41.8 lb/ft3 670 kg/m3
Crook	10' 12': Max. 10mm (²⁵ / ₆₄ ") 14' 16': Max. 13mm (³³ / ₆₄ ")

Hardness (Janka) 1618 lb 7.2 kN

Fire Rating

Class B as per ASTM Designation E84-15a, "Standard Method of Test for Surface Burning Characteristics of Building Materials".

Dimensional Stability (Swelling/Shrinkage)

Maximum Swelling (dry to wet, tangential direction): 4%

NOTE

If machining reveals surface areas significantly paler in colour, that board, or the affected portion of the board, shall be discarded if the width of the pale area is more than 3 cm. Such areas may be insufficiently treated, and may therefore fail to meet Kebony's durability criteria. Follow the Kebony Milling and Machining Guidelines when working with Kebony.

CERTIFICATIONS

FSC® SCS-COC-008513 - www.fsc.org EPD: NEPD-407-287-EN - www.epd-norge.no ICC ESR-3756 - www.icc-es.org







EXAMPLE OF WEATHERING



DISCLAIMER

Kebony products will change in appearance when exposed to rain and sun. Color changes and surface cracks will occur due to natural weathering. Kebony cannot be held liable for any such variations in colour and surface appearance. This will not influence durability and overall performance of the product.

Kebony is continuously working on product development. Information in this datasheet may be changed without further notice.

Up to 5% of the delivered boards may be outside this specification.