

2x4 Clear Rough Sawn / #2423



Actual Dimensions: 2" x 4" *

Lengths: Up to 16' **

* Width and thickness are nominal measures

Actual dimension can be slightly larger

** Lengths vary based on availability

Quality & Appearance Upon Delivery

Knots/Pitch Pockets May be visible and are a natural occurrence in wood

Cracks Surface cracks and checks may be visible

Wane May be visible on rough sawn products

Moisture Content 4-8%

Cupping Max. 2% of width

Density 41.8 lb/ft³
670 kg/m³

Crook 10' 12': Max. 10mm (²⁵/₆₄"")
14' 16': Max. 13mm (³³/₆₄"")

Hardness (Janka) 1618 lb
7.2 kN

Fire Rating

Class B as per ASTM Designation E84-15a, "Standard Method of Test for Surface Burning Characteristics of Building Materials".

Dimensional Stability (Swelling/Shrinkage)

Maximum Swelling (dry to wet, tangential direction): 4%

NOTE

If machining reveals surface areas significantly paler in colour, that board, or the affected portion of the board, shall be discarded if the width of the pale area is more than 3 cm. Such areas may be insufficiently treated, and may therefore fail to meet Kebony's durability criteria. Follow the Kebony Milling and Machining Guidelines when working with Kebony.

CERTIFICATIONS

FSC® SCS-COC-008513 - www.fsc.org

EPD: NEPD-407-287-EN - www.epd-norge.no

ICC ESR-3756 - www.icc-es.org



EXAMPLE OF WEATHERING



DISCLAIMER

Kebony products will change in appearance when exposed to rain and sun. Color changes and surface cracks will occur due to natural weathering. Kebony cannot be held liable for any such variations in colour and surface appearance. This will not influence durability and overall performance of the product.

Kebony is continuously working on product development. Information in this datasheet may be changed without further notice.

Up to 5% of the delivered boards may be outside this specification.