
www.kebony.us | 833.795.8660 | info@kebony.us

# 2x3 Clear Beam S4S E4E / #2480



Actual Dimensions: 1 1/2" x 2 17/25"

Lengths: 10', 12', 14', 16'

## Quality & Appearance Upon Delivery

Knots/Pitch Pockets	May be visible and are a natural occurrence in wood	Crook	10' 12': Max. 10mm ( <sup>25</sup> / <sub>64</sub> ") 14' 16': Max. 13mm ( <sup>33</sup> / <sub>64</sub> ")
Cracks	Surface cracks and checks may be visible	Hardness (Janka)	1618 lb 7.2 kN
Wane	Max. 1/3 of thickness and width	Fire Rating Class B as per ASTM Designation E84-15a, "Standard Method of Test for Surface Burning Characteristics of Building Materials".	
Moisture Content	4-8%		
Cupping	Max. 2% of width		
Density	41.8 lb/ft3 670 kg/m3	Dimensional Stability (Swelling/Shrinkage)  Maximum Swelling (dry to wet, tangential direction): 4%	

#### **CERTIFICATIONS**

FSC® SCS-COC-008513 - www.fsc.org EPD: NEPD-407-287-EN - www.epd-norge.no





### **EXAMPLE OF WEATHERING**



#### **DISCLAIMER**

Kebony products will change in appearance when exposed to rain and sun. Color changes and surface cracks will occur due to natural weathering. Kebony cannot be held liable for any such variations in colour and surface appearance. This will not influence durability and overall performance of the product.

Kebony is continuously working on product development. Information in this datasheet may be changed without further notice.

Up to 5% of the delivered boards may be outside this specification.