

## 2x6 Clear Rough Sawn / #2489



Actual Dimensions: 2" x 6" \*

Lengths: Up to 16' \*\*

\* Width and thickness are nominal measures

Actual dimension can be slightly larger

\*\* Lengths vary based on availability

### Quality & Appearance Upon Delivery

**Knots/Pitch Pockets** May be visible and are a natural occurrence in wood

**Cracks** Surface cracks and checks may be visible

**Wane** May be visible on rough sawn products

**Moisture Content** 4-8%

**Cupping** Max. 2% of width

**Density** 41.8 lb/ft<sup>3</sup>  
670 kg/m<sup>3</sup>

**Crook** 10' 12': Max. 10mm (<sup>25</sup>/<sub>64</sub>"")  
14' 16': Max. 13mm (<sup>33</sup>/<sub>64</sub>"")

**Hardness (Janka)** 1618 lb  
7.2 kN

#### Fire Rating

Class B as per ASTM Designation E84-15a, "Standard Method of Test for Surface Burning Characteristics of Building Materials".

#### Dimensional Stability (Swelling/Shrinkage)

Maximum Swelling (dry to wet, tangential direction): 4%

#### NOTE

If machining reveals surface areas significantly paler in colour, that board, or the affected portion of the board, shall be discarded if the width of the pale area is more than 3 cm. Such areas may be insufficiently treated, and may therefore fail to meet Kebony's durability criteria. Follow the Kebony Milling and Machining Guidelines when working with Kebony.

#### CERTIFICATIONS

FSC® SCS-COC-008513 - [www.fsc.org](http://www.fsc.org)

EPD: NEPD-407-287-EN - [www.epd-norge.no](http://www.epd-norge.no)

ICC ESR-3756 - [www.icc-es.org](http://www.icc-es.org)



#### EXAMPLE OF WEATHERING



#### DISCLAIMER

Kebony products will change in appearance when exposed to rain and sun. Color changes and surface cracks will occur due to natural weathering. Kebony cannot be held liable for any such variations in colour and surface appearance. This will not influence durability and overall performance of the product.

Kebony is continuously working on product development. Information in this datasheet may be changed without further notice.

Up to 5% of the delivered boards may be outside this specification.