

## 1x6 Clear Kebony Cladding Board / #2682



Actual Dimensions:  $1\frac{3}{16}" \times 5\frac{1}{16}"$   
Lengths: 10', 12', 14', 16'

### Quality & Appearance Upon Delivery

**Moisture Content** 4-8%

**Cupping** Max. 1% of width

**Density**  
(12% mc) 41.8 lb/ft<sup>3</sup>  
670 kg/m<sup>3</sup>

**Crook** 10' 12': Max. 10mm ( $2\frac{5}{64}"$ )  
14' 16': Max. 13mm ( $3\frac{3}{64}"$ )

**Cracks** Surface cracks and checks may be visible

**Wane** May occur on the back

#### Fire Rating

Class B as per ASTM Designation E84-15a, "Standard Method of Test for Surface Burning Characteristics of Building Materials".

**Hardness (Janka)** 1618 lb  
7.2 kN

#### Knots/Pitch pockets

May be visible and are a natural occurrence in wood

#### Dimensional Stability (Swelling/Shrinkage)

Maximum Swelling (dry to wet, tangential direction): 4%

NOTE: There may be defects on the back side. These will not affect the technical quality of the product. This board is not reversible.

### CERTIFICATIONS

FSC® SCS-COC-008513 - [www.fsc.org](http://www.fsc.org)

EPD: NEPD-407-287-EN - [www.epd-norge.no](http://www.epd-norge.no)



### EXAMPLE OF WEATHERING



### DISCLAIMER

Kebony products will change in appearance when exposed to rain and sun. Color changes and surface cracks will occur due to natural weathering. Kebony cannot be held liable for any such variations in colour and surface appearance. This will not influence durability and overall performance of the product.

Kebony is continuously working on product development. Information in this datasheet may be changed without further notice.

Up to 5% of the delivered boards may be outside this specification.