


1x6 Clear 90 Degree Shiplap / #K90XX514



Face: 5 3/4"

Actual Dimensions: 3/4" x 5 3/4"

Lengths: 10', 12', 14', 16'

Quality & Appearance Upon Delivery

Knots/Pitch Pockets May be visible and are a natural occurrence in wood

Cracks Surface cracks and checks may be visible

Wane May occur on the back

Moisture Content 4-8%

Cupping Max. 2% of width

Density 41.8 lb/ft³
670 kg/m³

Crook 10' 12': Max. 10mm (25/64")
14' 16': Max. 13mm (33/64")

Hardness (Janka) 1618 lb
7.2 kN

Fire Rating
Class B as per ASTM Designation E84-15a, "Standard Method of Test for Surface Burning Characteristics of Building Materials".

Dimensional Stability (Swelling/Shrinkage)
Maximum Swelling (dry to wet, tangential direction): 4%

NOTE
There may be defects on the back side. These will not affect the technical quality of the product. The board is not reversible.

CERTIFICATIONS

FSC® SCS-COC-008513 - www.fsc.org

EPD: NEPD-407-287-EN - www.epd-norge.no



EXAMPLE OF WEATHERING



DISCLAIMER

Kebony products will change in appearance when exposed to rain and sun. Color changes and surface cracks will occur due to natural weathering. Kebony cannot be held liable for any such variations in colour and surface appearance. This will not influence durability and overall performance of the product.

Kebony is continuously working on product development. Information in this datasheet may be changed without further notice.

Up to 5% of the delivered boards may be outside this specification and must be accepted.