



Natural wood
Made to last

Enhanced Wood Technologies Inc.
833.795.8660
info@kebony.us
www.kebony.us

Kebony Clear (Radiata) SR and SRI Values

Solar Reflectivity

Sample #	Solar Reflectivity
1	0.329
2	0.326
3	0.333
Average	0.329

Solar Reflectance Index

		Low	Medium	High
		5	12	30
Sample ID	Sample Descriptor	Solar Reflectance Index		
K01	Kebony Radiata	49.1	49.3	49.4